



AAMA Architectural Specifications

	AAMA 2603-02	AAMA 2604-02	AAMA 2605-02
Pretreatment	Not specified	—Chrome(30 mg/ft ²) —non-chrome allowed	Chrome (40 mg/ft ²)
Film Thickness, min.	0.8 mil	1.2 mil	1.2 mil
Pencil Hardness, min	H	F	F
Abrasion Resistance, min.	Not specified	20	40
Humidity Resistance, hrs.	1500	3000	4000
Salt Spray Resistance, hrs.	1500	3000	4000
Weathering	1 year South Florida	5 year South Florida	10 year South Florida
Color Retention	Minimal change	Less than 5ΔE	Less than 5ΔE
Gloss Retention	Minimal change	> 30 %	> 50 %
Spraylat Product		ARC 2001	NEWLAR

Powder Coatings